TECHNICAL DATA SHEET



Ref. No: UTD-158: Issue Date:01.01.2004 Revision Date:12.03.2024 Page:1/

UNIRUBBER PLUS 367-40 Elastic Acrylic Latex Based Resilience Coating

UNIRUBBER PLUS 367-40

Elastic Acrylic Latex Based Resilience Coating

Product Characteristics

%100 acrylic latex based rubber granules filled cushion coating for tennis court flooring systems.

Advantages

- Ready to use
- Gives higher thickness
- High resilience
- Perfect elasticity
- Easy application.
- Easy mixing at work site.
- Cost effective.

Product Use

UNIRUBBER PLUS 367-40 is a elastic resilience undercoat that can be applied on Resurfacer for Acryflex T Tennis Court System.

Colours: Black

Product Properties (at 20°C)

Mass Density (appox.)	0,96 gr/cm ³
Solids Content (% Weight)	58
Touch After Dry	1-1½ h
Overcoating Interval	Minimum 3h
Therotical Consumption	0,450 kg/m2 (for each layer)

Processing Procedure

- Surfaces should be cleaned from grease, salts, debris, dust and any other contaminants.
- UNIRUBBER PLUS 367-40 should be applied after Acrylic Resurfacer 367-30
- UNIRUBBER 367-40 should be applied after UNIRUBBER PLUS 367-40 to get more smooth and homogenic surface.

Application Procedure

• First, water should be added to UNIRUBBER PLUS 367-40. Mix well by a slow speed mixer till getting homogenous mixing.













TECHNICAL DATA SHEET



Ref. No: UTD-1585 Issue Date:01.01.2004 Revision Date:12.03.2024 Page:1/2

UNIRUBBER PLUS 367-40 Elastic Acrylic Latex Based Resilience Coating

Mixing ratios are as below;

UN	NIRUBBER PLUS 367-40	50 kg
*V	Vater	5 kg

^{*}Water amount can be vary depend on ambient temperature. At hot weathers may be added %5 more water.

CONSUMPTION

Theoretical spreading rate:0,450 kg/m² (Depending on surface permeability and porosity)per each coat. As requested can be applied 2-5 layers by using rubber blade squeege Do not apply the material if temperature less than 14° C or over than 35° C.

Important Note

Coverage rates may vary depending on the surface porosity, ambient temperature and application technique.

Packing

50 kg in Polyethylene drums or 180 kg in steel drums.

Storage

The product must be stored in sealed drums placed at indoor, dry warehousing spaces within the temperature range from 15° C to 35° C. Shelf life (warranty) is 12 months from the production date in cool and dry place. Don't leave the products outdoor exposed to the sun.

Safety & Related Data

UNIRUBBER PLUS 367-40 is not hazardous and no contains formaldehyde, asbestos, mercury, lead or chromate and derivatives. Product contains fire retardant addidtives. For detailed information related to safe gandling, occupational health and safety at work, please see the relevant product safety data sheet (MSDS).

Note

The statements made on this technical sheet are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.











