

ACRYLIC PRIMER 367-28

%100 Pure Acrylic latex based Primer for asphalt sub base

ACRYLIC PRIMER 367-28

Product Characteristics

%100 Pure Acrylic latex based Primer for asphalt sub base

Product Use

Acrylic Primer 367-28 is a adhesion primer that bonds asphalt and resurfacer layer for Acryflex T Tennis Court System.

Advantages

- Ready to use
- 0 VOC product
- Easy application
- Sprayable
- Fast drying

Product Properties (at 20° C)

Mass Density (approx.)	1,06 gr/cm ³
Solids Content (% Weight)	28
Touch After Dry	30 min
Overcoating Interval	Minimum 2 h
Therotical Consumption	0,150 kg/m ² (1Layer)

Processing Procedure

- Surfaces should be cleaned from grease, salts, debris, dust and any other contaminants.
- Over uncoated Asphalt, Acrylic Primer 367-28(Acrylic Primer) should be applied before Acrylic Resurfacer 367-30, PRECOAT 367-200, PRECOAT 367-43, PAVERCOAT 43 2K

Application Procedure

No any special procedure, The product is ready to apply, apply with roll, brush or spray.

Do not apply the material if temperature less than 14° C or over than 35° C.

ACRYLIC PRIMER 367-28

%100 Pure Acrylic latex based Primer for asphalt sub base

Ref. No: UTD-1500
Issue Date:01.01.2004
Revision Date:12.03.2024
Page:1/2**Important Note**

Coverage rates may vary depending on the surface porosity, ambient temperature and application technique.

Packing

50 kg in Polyethylene drums or 180 kg in steel drums.

Storage

The product must be stored in sealed drums placed at indoor, dry warehousing spaces within the temperature range from 15° C to 35° C. Shelf life (warranty) is 12 months from the production date in cool and dry place. Don't leave the products outdoor exposed to the sun.

Safety & Related Data

Acrylic Primer 367-28 is not hazardous and no contains formaldehyde, asbestos, mercury, lead or chromate and derivatives. Product contains fire retardant addittives. For detailed information related to safe gandling, occupational health and safety at work, please see the relevant product safety data sheet (MSDS).

Note

The statements made on this technical sheet are believed to be true and accurate, and are intended to provide a guide for approved construction practices. UNİCA does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. UNİCA warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNİCA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNİCA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.