

PRECOAT 367-200 WOS NEUTRAL

Concentrated Pure Acrylic Latex Based Topcoat

PRECOAT 367-200 WOS NEUTRAL

Concentrated Pure Acrylic Latex Based Topcoat.

Product Characteristics

%100 Concentrated acrylic latex based topcoat for tennis court flooring systems.

Advantages

- Neutral colour, can be coloured with desired colorants.
- Less stock costs.
- Easy mixing at work site.
- Cost effective.

Product Use

Precoat 367-200 WOS NEUTRAL is a concentrated topcoat that can be applied on Resurfacer or Cushion layers for Acryflex T Tennis Court System.

Colour : Light Brownish(neutral)

Product Properties (at 20° C)

Mass Density (approx.)	1,22 gr/cm ³
Solids Content (% Weight)	48
Touch After Dry	1-1½ h
Overcoating Interval	Minimum 3h
Theoretical Consumption	0,300 kg/m ² (as concentrated 1Layer)

Processing Procedure

- Surfaces should be cleaned from grease, salts, debris, dust and any other contaminants.
- Precoat 367-200 WOS NEUTRAL should be applied after Acrylic Resurfacer/LW 367-30 or UNIRUBBER/LW 367-40.

Application Procedure

First, suitable grade silica sand or quartz should be added to Precoat 367-200 WOS and desired coloured pigmet paste+ tap water. Mix well by a slow speed mixer till getting homogenous mixing.

TECHNICAL DATA SHEET



PRECOAT 367-200 WOS NEUTRAL Concentrated Pure Acrylic Latex Based Topcoat

Ref. No: UTD-1560
Issue Date:01.01.2004
Revision Date:12.03.2024
Page:1/2

Mixing ratios are as below;

Precoat 367-200 WOS NEUTRAL	75 kg
Silica Sand/Quartz(0,1-0,3 mm)	45 kg
Water*	12 kg
Coloured Pigment Paste**	5 kg

*Water amount can be vary depend on ambient temperature. At hot weathers may be added %5 more water.

**Pigment Paste Colours : Unica Red, Terracota Red, Bosphorus Blue, Sky Blue, Grass green, Moss Green, Stone Grey, Beige, Forest Green, Unica Violet, Deep Blue, Magenta, Unica Blue, Open Blue, Ocean Blue(Upon request special colours can be produced).

CONSUMPTION

Theoretical spreading rate:0,450 kg/m² (Depending on surface permeability and porosity)per each coat. 0,800 kg-1 kg /sqm (depends on surface quality) as 2 layers by using rubber blade squeegee Do not apply the material if temperature less than 14° C or over than 35° C.

Important Note

Coverage rates may vary depending on the surface porosity, ambient temperature and application technique.

Packing

75 kg in Polyethylene drums or 200 kg in steel drums.

Storage

The product must be stored in sealed drums placed at indoor, dry warehousing spaces within the temperature range from 15° C to 35° C. Shelf life (warranty) is 12 months from the production date in cool and dry place. Don't leave the products outdoor exposed to the sun.

Safety & Related Data

PRECOAT 367-200 WOS NEUTRAL is not hazardous and no contains formaldehyde, asbestos, mercury, lead or chromate and derivatives. Product contains fire retardant additives. For detailed information related to safe handling, occupational health and safety at work, please see the relevant product safety data sheet (MSDS).

Note

The statements made on this technical sheet are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.



BOYTEM BOYA VE KİMYA SANAYİ TİCARET LİMİTED ŞİRKETİ

Factory: Gümüşova OSB. 1.Sk No:4 İç Kapı No:1 Gümüşva Düzce TÜRKİYE

www.unicaboya.com - info@unicaboya.com

T: +90 216 304 03 05 F: +90 216 304 12 15

