# **TECHNICAL DATA SHEET**



Ref. No: UTD-1530 Issue Date:01.01.2004 Revision Date:12.03.2024 Page:1/1

# GLOSSCOAT 367-TIX %100 Pure Acrylic Latex Based Clear Drying Protective Sealer

#### **GLOSSCOAT 367-TIX**

Product Characteristics %100 Pure Acrylic Latex Based Clear Drying Protective Sealer

#### **Product Use**

Glosscoat 367-TIX is a pure acrylic special formulated clear drying protective topcoat/sealer for Acryflex T Tennis Court or PAVERCOAT 43 2K cycle&walking path systems.

#### Advantages

- Ready to use
- 0 VOC product
- Easy application
- Thixrotropic
- Fast drying
- Ultra Matt
- Water repellent
- Perfect scratch resistant.

## Product Properties (at 20°C)

Mass Density (appox.)	0,93 gr/cm <sup>3</sup>
Solids Content (% Weight)	39
Touch After Dry	30 min
Overcoating Interval	Minimum 2 h
Therotical Consumption	0,150-0,200 kg/m2 (1Layer)

#### **Processing Procedure**

- Surfaces should be cleaned from grease, salts, debris, dust and any other contaminants.
- Should be applied onto all kind acrylic topcoat sport floorings.

### **Application Procedure**

No any special procedure, product is ready to use, apply with roll, brush or spray.

Do not apply the material if temperature less than 14° C or over than 35° C.













# TECHNICAL DATA SHEET



Ref. No: UTD-1530 Issue Date:01.01.2004 Revision Date:12.03.2024 Page:1/2

# GLOSSCOAT 367-TIX Revision D %100 Pure Acrylic Latex Based Clear Drying Protective Sealer

#### **Important Note**

Coverage rates may vary depending on the surface porosity, ambient temperature and application technique.

**Packing** 

50 kg in Polyethylene drums or 180 kg in steel drums.

Storage

The product must be stored in sealed drums placed at indoor, dry warehousing spaces within the temperature range from 15° C to 35° C. Shelf life (warranty) is 12 months from the production date in cool and dry place. Don't leave the products outdoor exposed to the sun.

Safety & Related Data

Glosscoat 367-TIX is not hazardous and no contains formaldehyde, asbestos, mercury, lead or chromate and derivatives. For detailed information related to safe gandling, occupational health and safety at work, please see the relevant product safety data sheet (MSDS).

Note

The statements made on this technical sheet are believed to be true and accurate, and are intended to provide a guide for approved construction practices. UNİCA does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. UNİCA warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall UNİCA be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or work performed. UNİCA shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.











